
(12) PATENT ABSTRACT (11) Document No. AU-A-70849/91
(19) AUSTRALIAN PATENT OFFICE

- (54) Title
EXAMINATION OF PHYSICAL PROPERTIES OF THIN FILMS
- International Patent Classification(s)
(51)³ G01N 021/65
- (21) Application No. : 70849/91 (22) Application Date : 08.02.91
- (30) Priority Data
- (31) Number (32) Date (33) Country
4004088 10.02.90 DE FEDERAL REPUBLIC OF GERMANY
- (43) Publication Date : 15.08.91
- (71) Applicant(s)
BASF AKTIENGESELLSCHAFT
- (72) Inventor(s)
WOLFGANG KNOLL; HARALD KNOBLOCH
- (74) Attorney or Agent
WATERMARK PATENT & TRADEMARK ATTORNEYS, Locked Bag 5, HAWTHORN VIC
3122
- (57) Claim

1. A method for examining the physical properties of thin films with the aid of polarized light, which comprises directing polarized light at a layer system, exciting plasmon surface polaritons therein and thereby creating Raman-scattered light within the layer or layer system under examination, and imaging said light on a detector using an imaging system.

15. A method as claimed in claim 1 for use in Raman spectroscopy, wherein the angle dispersion of plasmon surface polaritons excited in the layer system under examination is utilized for the spectral resolution of the Raman lines.

(CONVENTION. By one or more persons and/or a Company.)

4 /
Form 4.

COMMONWEALTH OF AUSTRALIA

Patents Act 1952-1969

CONVENTION APPLICATION FOR A PATENT

(1) Here
insert (in
full) Name
or Names of
Applicant or
Applicants,
followed by
Address(es).

X⁽¹⁾ BASF AKTIENGESELLSCHAFT
We of D-6700 Ludwigshafen, Federal Republic of Germany

(2) Here
insert Title
of Invention.

hereby apply for the grant of a Patent for an invention entitled:⁽²⁾

EXAMINATION OF PHYSICAL PROPERTIES OF THIN FILMS

(3) Here insert
number(s)
of basic
application(s).

which is described in the accompanying complete specification. This application is a
Convention application and is based on the application numbered:⁽³⁾

P40 04 088.7

(4) Here insert
Name of basic
Country or
Countries, and
basic date or
dates.

for a patent or similar protection made in:⁽⁴⁾ Federal Republic of Germany
on 10th February 1990

~~My~~
Our address for service is WATERMARK PATENT & TRADEMARK ATTORNEYS
290 Burwood Road, Hawthorn, Victoria, Australia.

DATED this7th..... day ofFebruary..... 1991.....

(5) Signa-
ture(s) of
Applicant(s)
or
Seal of
Company and
Signatures of
its Officers as
prescribed by
its Articles of
Association.

by (s)

BASF AKTIENGESELLSCHAFT

.....Louis.C..Gebhardt.....

Registered Patent Attorney

To: THE COMMISSIONER OF PATENTS.

(CONVENTION. Company.)

COMMONWEALTH OF AUSTRALIA

Patents Act 1952-1962

DECLARATION IN SUPPORT OF A CONVENTION
APPLICATION FOR A PATENT OR PATENT OF ADDITION(1) Here
insert (in
full) Name of
Company.In support of the Convention Application made by⁽¹⁾BASF Aktiengesellschaft, a German Joint Stock Company of
6700 Ludwigshafen, Federal Republic of Germany;(2) Here
insert title
of invention.(hereinafter referred to as the applicant) for a Patent
for an invention entitled:⁽²⁾

Examination of physical properties of thin films

(3) Here
insert full Name
and Address
of Company
official
authorized
to make
declaration.(3) ~~xx~~ We, GUNTHER WELZEL and PETER BARZ, citizens of the
Federal Republic of Germany, residing, respectively, at
Auf dem Koepfel, 6702 Bad Duerkheim; and 20 Hochfeldstrasse,
6700 Ludwigshafen; Federal Republic of Germany;

do solemnly and sincerely declare as follows:

1. ~~xx~~ We are
authorised by the applicant for the patent
to make this declaration on its behalf.2. The basic application as defined by Section 141 of the Act was
made in⁽⁴⁾ the Federal Republic of Germany under No.
P 40 04 088.7 on the 10th day of February 1990 .
by BASF Aktiengesellschaftby ~~xxxxxx~~ ~~xxxxxx~~ ~~xxxxxx~~(5) Here
insert (in
full) Name
and Address
of Actual
Inventor or
Inventors.

3. (5) WOLFGANG KNOLL, HARALD KNOBLOCH,

citizens of Federal Republic of Germany, residing, respectively, at
18d Elsa-Brandstroem-Strasse, 6500 Mainz; 16 Gartenstrasse,
6509 Albig; Federal Republic of Germany;We/are the actual inventors of the invention and the facts upon which the applicant
is entitled to make the application are as follow:

The applicant is the assignee of the invention from the said

WOLFGANG KNOLL, HARALD KNOBLOCH,

4. The basic application -

COMMONWEALTH OF AUSTRALIA

PATENTS ACT 1952-69

COMPLETE SPECIFICATION

(ORIGINAL)

Class

Int. Class

Application Number:

Lodged:

Complete Specification Lodged:

Accepted:

Published:

Priority :

Related Art :

Name of Applicant : BASF AKTIENGESELLSCHAFT

Address of Applicant : D-6700 Ludwigshafen, Federal Republic of Germany

Actual Inventor : WOLFGANG KNOLL and HARALD KNOBLOCH

Address for Service : WATERMARK PATENT & TRADEMARK ATTORNEYS.
LOCKED BAG NO. 5, HAWTHORN, VICTORIA 3122, AUSTRALIA

Complete Specification for the invention entitled:

EXAMINATION OF PHYSICAL PROPERTIES OF THIN FILMS

The following statement is a full description of this invention, including the best method of performing it known to :- US

Examination of physical properties of thin films

5 The present invention relates to a method for examining physical properties of thin films with the aid of polarized light by using polarized light to excite plasmon surface polaritons in a layer system. The method according to the present invention makes it possible to carry out Raman-spectroscopic examinations with minimal hardware.

10 Plasmon surface polaritons (PSPs) are bound, non-radiative, electromagnetic modes which propagate along a metal/dielectric interface. Their field strength is at a maximum at the metal surface and decays exponentially not only into the metal but also into the dielectric (cf. H. Raether, in Physics of Thin Films Vol. 9, 145-261, New York 1977).

15 The interest in plasmon surface polaritons has increased in recent years, since they can be successfully used for field enhancement in the various surface-spectroscopic examinations of adsorbates and ultrathin films/layer systems (cf. R.M. Corn, M.R. Philpott, J. Chem. Phys. 80 (1984), 5245-49).

20 Raman scattering is a light scattering method in which the spectral position and intensity of the non-resonantly scattered light (here PSP) provides information about the molecular structure of the examined sample (cf. Knobloch, Duschl, Knoll, J. Chem. Phys. 91 (1989), 3810-14); Raman-scattered light is shifted in the spectrum compared with the incident light (Stokes shift).

25 It is an object of the present invention to provide a method which makes it possible to carry out Raman-spectroscopic examinations of ultrathin films/layer systems with a minimum of optical components.

30 Whereas the existing methods for Raman-spectroscopic examinations require specific equipment for spectral analysis, for example monochromators, the method according to the present invention makes it possible to dispense with a monochromator or similar equipment for

spectral analysis.

The method according to the present invention makes it possible to image the Raman-scattered light from the layer/layer system under examination directly on a camera with a lens. This is accomplished using surface-enhanced Raman spectroscopy by utilizing the angle dispersion and polarizing properties of plasmon surface polaritons (cf. Knoll et al., J. Chem. Phys. 77 (1982), 2254).

We have found, surprisingly, that the stated object is achieved by a method for the Raman-spectroscopic examination of ultrathin layers/layer systems (thickness $< 0.1 \mu\text{m}$) wherein the layers under examination have been applied to a solid support and are examined by means of surface-enhanced Raman spectroscopy as a function of the angle of incidence and the angle of observation

The present invention accordingly provides a method for examining the physical properties of thin films with the aid of polarized light, which comprises directing polarized light at a layer system, exciting plasmon surface polaritons therein and thereby creating within Raman-scattered light the layer or layer system under examination, and imaging said light on a detector using an imaging system.

The plasmon surface polaritons are in general excited at a metal/ or semiconductor/dielectric interface.

To excite plasmon surface polaritons, the coupler used is in particular a prism or a grid structure on a solid surface.

In preferred embodiments of the method according to the present invention, a metal or semiconductor layer or the layer or layer system under examination is mounted on the coupler, or a metal or semiconductor layer and the layer under examination have been mounted on a solid support and this solid support has been disposed at a

distance of 100-400 nm from the base of a prism.

The imaging system used is preferably a collecting lens, a lens system or a microscope objective.

It is advantageous to use a two-dimensional detector, in particular a low-noise camera, especially a
5 CCD camera whose CCD chip is cooled with liquid nitrogen.

The present invention also provides a method for imaging the structured layer system under examination in the Raman-shifted region of the spectrum by imaging the
10 structure of the layer under examination by utilizing the angle dispersion of plasmon surface polaritons as contrast mechanism, and also for the use of the method according to the present invention for Raman spectroscopy, wherein the angle dispersion of plasmon surface polaritons excited in the layer system under examination is utilized for the spectral resolution of the Raman lines.

The method according to the present invention is thus suitable not only for Raman-spectroscopic examination but also for imaging low-contrast but Raman-active samples of any kinds of thin organic films, for example lipid monolayers, cadmium arachidate, polyglutamates and polysilanes.
15
20

Plasmon surface polaritons are in general excited with a coupler in an Otto, Kretschmann or grid configuration using monochromatic, parallel, polarized light. The light source used is preferably an argon ion laser.
25

In the grid configuration, the layer/layer system under examination is applied to a metal or semiconductor layer whose surface has a grid structure. The grid structure is applied to the surface of the underlying glass substrate, preferably by means of holographic or lithographic techniques.
30

The coupling conditions for the exciting light beam and also for the Stokes-shifted Raman-scattered light are determined by the angle dispersion properties of the PSPs.
35

The spectral analysis of the Raman-scattered light is effected using the angle dispersion properties of the PSPs.

5 The thickness of the layer or layer systems under examination is in general $< 0.1 \mu\text{m}$, preferably $< 50 \text{ nm}$, for example within the range from 5 to 40 nm.

10 Using the method according to the present invention it is possible to examine the following properties of thin, in particular ultrathin, films: optical layer thickness ($n \times d$), refractive index (n) and, particularly advantageously, the molecular polarizabilities of the layer under examination (for example monomolecular films and multilayer assemblies).

15 The layer or layer system under examination can be applied to metal or semiconductor layers in a conventional manner, for example by the Langmuir-Blodgett technique, by spin coating from solution, by vapor deposition and/or by adsorption from the gas or liquid phase, suitable metal layers being in general for example gold and in particular silver layers.

20 The Langmuir-Blodgett technique for fabricating thin films and multilayer assemblies is described for example in the paper by H. Kuhn, D. Möbius and H. Bücher in Physical Methods of Chemistry, eds. A. Weissberger and B.W. Rossitter (Wiley, N.Y. 1972), part III B, chapter VII.

25 To this end, the solution of the substance to be examined, for example a lipid, in a low-boiling organic solvent, for example chloroform, is spread out at the water/air interface and, after the solvent has evaporated, is transferred in a conventional manner by the Langmuir-Blodgett technique to a metallic layer of a solid base material, for example a microscope slide made of glass which has been coated with silver and has been
30 appropriately structured, for example with a holographic grid of a certain periodicity and modulation.

35 In addition, a system of optical filters can be

used for spectral analysis and/or for suppressing scattered light.

The construction of the apparatus used according to the present invention is depicted in diagrammatic form in Figure 1, where 1 denotes the incident laser beam, 2 the Raman-scattered light, 3 the lens (a microscope objective), 4 the detector (CCD camera), 5 the layer under examination, 6 the metal layer, and 7 the microscope slide with a grid structure.

The sample prepared by the abovementioned methods is examined by means of PSP-enhanced Raman spectroscopy, meaning that the PSPs become coupled to the incident light via the grid/prism and are Raman-scattered. This Raman-scattered light is imaged by means of a lens onto a CCD camera, preferably cooled with liquid nitrogen, and recorded and can be stored for example on magnetic data media.

Suitable CCD cameras are described for example in D.N. Batchelder, ESN European Spectroscopy News, 80 (1988), 28-33. The method according to the present invention makes it possible to image the Raman-scattered light from the layer under examination directly on a camera.

EXAMPLE 1

8 layers of cadmium arachidate (CdA) are applied by the Langmuir-Blodgett technique to a microscope slide whose surface, which bears a holographic grid (periodicity: $0.5 \mu\text{m}$, modulation 5 nm), has been vapor-deposited with a 100 nm thick coating of silver.

Using a UV lamp and a mask, a 1 mm wide stripe is desorbed off the sample (irradiation time: 30 minutes).

The light from the argon ion laser ($\lambda = 476.5 \text{ nm}$) couples to the polaritons at an angle of incidence of 20° . The Raman-scattered light is collected by means of a lens at an angle of observation of 2° and is imaged through a monochromator on a nitrogen-cooled CCD camera. The image recorded with the CCD camera permits clear

distinction between coated and desorbed areas.

If the incident light beam does not satisfy the PSP coupling conditions, it is impossible to discern any image, let alone any surface structure.

5 If the experimental setup is as above and the sample is prepared as above except that the CdA is half deuterated and half protonated, the image obtained on the CCD camera permits a clear distinction between protonated and deuterated areas.

10 It is thus possible to produce a contrast between the materials, despite the fact that the optical properties of the two materials are the same.

EXAMPLE 2

15 16 layers of cadmium arachidate (CdA) are applied by the Langmuir-Blodgett technique to a microscope slide whose surface, which bears a holographic grid (periodicity: $0.5 \mu\text{m}$, modulation: 5 nm), has been vapor-deposited with a 100 nm thick coating of silver. The layer system thus prepared is structured through a mask by means of UV
20 desorption (mercury vapor lamp exposure for 1 hour).

The light from the argon ion laser ($\lambda = 476.5 \text{ nm}$) couples with the polariton field at an angle of incidence of 24° . The Raman-scattered light is imaged at an angle of observation of 6° by means of a lens system and a
25 system of filters (long pass: Schott OG 515; interference filter: Pörschke TCV-072) on a nitrogen-cooled CCD camera.

The image recorded with the CCD camera clearly reveals coated and desorbed areas.

30 If the incident light beam does not satisfy the PSP coupling conditions, it is impossible to discern any image, let alone any surface structure.

A laser beam is incident upon the sample layer system under examination at a PSP resonance angle θ_1 , so
35 that PSPs and the incident light are optimally coupled. The surface structure of the sample is imaged at an angle of observation θ_0 , through a lens and filter system,

directly on a CCD camera.

A suitable setup is shown in Figure 2, where 1 denotes the sample (a layer system), 2, 4 and 5 each denote lenses, 3 denotes a diaphragm, 6 denotes a filter (filter system), and 7 denotes the CCD camera.

Figure 3 shows the dispersion of plasmon surface polaritons in grid coupling, where $\bar{\nu}$ (laser) denotes the wavenumber of the incident laser light, $\bar{\nu}$ (Raman) denotes the wavenumber of the Raman-scattered light, θ_i denotes the PSP resonance angle for incident laser light, and θ_o denotes the angle of observation or the PSP resonance angle for Raman-scattered light.

THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:
~~WE CLAIM:~~

1. A method for examining the physical properties of thin films with the aid of polarized light, which comprises directing polarized light at a layer system, exciting plasmon surface polaritons therein and thereby creating Raman-scattered light within the layer or layer system under examination, and imaging said light on a detector using an imaging system.
2. A method as claimed in claim 1, wherein plasmon surface polaritons are excited at a metal/or semiconductor/dielectric interface.
3. A method as claimed in claim 2, wherein plasmon surface polaritons are excited using a coupler.
4. A method as claimed in claim 3, wherein the coupler used is a prism.
5. A method as claimed in claim 3, wherein the coupler used is a grid structure on a solid surface.
6. A method as claimed in claim 3, wherein a metal or semiconductor layer or the layer or layer system under examination is mounted on the coupler.
7. A method as claimed in claim 3, wherein a metal or semiconductor layer and the layer under examination have been mounted on a solid support and this solid support has been disposed at a distance of from 100 to 400 nm from the base of a prism.
8. A method as claimed in claim 4, wherein a metal or semiconductor layer and the layer under examination have been mounted on a solid support and this solid support has been disposed at a distance of from 100 to 400 nm from the base of a prism.
9. A method as claimed in claim 1, wherein in addition a system of optical filters is used to suppress scattered light.
10. A method as claimed in claim 1, wherein the imaging system used is a collecting lens, a lens system or a microscope objective.
11. A method as claimed in claim 1, wherein the

detector is two-dimensional.

12. A method as claimed in claim 10, wherein the detector is a low-noise camera.

13. A method as claimed in claim 11, wherein the camera is a CCD camera whose CCD chip is cooled with liquid nitrogen.

14. A method as claimed in claim 1, wherein, to image the structured layer system under examination in the Raman-shifted region of the spectrum, the structure of the layer under examination is imaged using the angle dispersion of plasmon surface polaritons as contrast mechanism.

15. A method as claimed in claim 1 for use in Raman spectroscopy, wherein the angle dispersion of plasmon surface polaritons excited in the layer system under examination is utilized for the spectral resolution of the Raman lines.

DATED this 7th day of February 1991.

BASF AKTIENGESELLSCHAFT

WATERMARK PATENT & TRADEMARK ATTORNEYS
"THE ATRIUM"
290 BURWOOD ROAD
HAWTHORN. VIC. 3122.